

AENOR

CTC-015 "Cementos"

CERTIFICADO DE EVALUACIÓN

ESTADÍSTICA DE LA PRODUCCIÓN

Empresa:

HEIDELBERG MATERIALS HISPANIA CEMENTOS S.A.

Fabrica:

AÑORGA

CEMENTO:

CEM I 52,5 R

UNE-EN 197-1:2011

Periodo estudiado:

01/2024 - 12/2024

Certificado AENOR:

015/002028

Este producto está certificado con la marca AENOR  para cementos. La Marca  es un distintivo de calidad de carácter voluntario acreditado por ENAC, según UNE-EN ISO/IEC 17065, que cumple con las exigencias recogidas en la Instrucción para la recepción de cementos en vigor. La evaluación estadística que se muestra a continuación corresponde a los resultados obtenidos en el periodo de estudio considerado.



CARACTERÍSTICAS DEL CEMENTO

ÍNDICE DE CONTRIBUCIÓN DEL PROCESO A LA SOSTENIBILIDAD (ICPS)

ÍNDICE DE CONTENIDO DE RECICLADO (IR) (%)

Índice de contenido de reciclado preconsumo (%)

Índice de contenido de reciclado postconsumo (%)

98
9,96
8,66
1,3

Composición Nominal declarada por el fabricante(%):

Clinker	Puzolana	Ceniza	Escoria	Caliza	Esquisto	Humo	Comp. Min.
98							2

CONTROL POR VARIABLES

Control de producción

Nº de muestras: 85

Especificación
Nº ensayos
Valor medio
Desviación típica
V. característico inf.
V. característico sup.

Resistencias (MPa)		Fraguados (min.)	
a 2 días	a 28 días	I.F.	F.F.
≥ 30	≥ 52,5	≥ 45	≤ 720
85	77	85	85
43,8	70	217	285
2,23	2,68	30	35
39,4	64,7	170	230
47,3	74,2	264	340

Especificación
Nº ensayos
Valor medio
Desviación típica
V. absoluto inferior
V. absoluto superior

Riesgo del consumidor < 3,25 %

Muestras de contraste

Nº de muestras: 10

Resistencias (MPa)		Fraguados (min.)	
a 2 días	a 28 días	I.F.	F.F.
≥ 30	≥ 52,5	≥ 45	≤ 720
10	10	10	10
42,5	67,8	232	321
1,67	3,29	37	39
39,77	63,05	170	255
45,7	72,08	280	385

CONTROL POR ATRIBUTOS (características físicas y químicas):

Control de producción

Nº de muestras: 85

Especificación
Nº de ensayos
Valor medio
Nº defectos
Nºdefectos admitidos

P.F. (%)	R.I. (%)	CL ⁻ (%)	SO3 (%)	EXP (mm)
≤ 5	≤ 5	≤ 0,1	≤ 4	≤ 10
85	20	20	85	43
2,9	1,3	0,05	3,12	0,2
0	0	0	0	0
4	0	0	4	1

Muestras de contraste

Nº de muestras: 10

Especificación
Nº de ensayos
Valor medio
Nº defectos
Nºdefectos admitidos

P.F. (%)	R.I. (%)	CL ⁻ (%)	SO3 (%)	EXP (mm)
≤ 5	≤ 5	≤ 0,1	≤ 4	≤ 10
10	10	10	10	10
2,62	0,73	0,02	3,15	0,5
0	0	0	0	0
0	0	0	0	0

Característica complementaria de Cr(VI) soluble en agua certificada según la norma UNE-EN 196-10 de acuerdo a lo establecido en el Reglamento (CE) nº 1907/2006, entrada 47. El contenido de Cr(VI) soluble en agua es conforme con el límite máximo de 0,0002% .En caso de usar agente reductor de Cr (VI) el cumplimiento de este requisito se ha evaluado al final de periodo de eficacia de dicho agente declarado por el fabricante.



Este informe tiene validez hasta el 1 de julio de 2025

Fdo: MIGUEL ANGEL MORALES RECIO
Fecha: 01/04/2025



AENOR CTC-015 "Cements"		CERTIFICATE OF STATISTICAL ASSESSMENT OF CEMENT PRODUCTION		
Company:	HEIDELBERG MATERIALS HISPANIA CEMENTOS S.A.			
Cement Plant:	AÑORGA			
CEMENT:	CEM I 52,5 R	UNE-EN 197-1:2011		
Evaluated period:	01/2024 - 12/2024	AENOR Certificate:		015/002028
This product holds the  ENOR marking. The  mark is a voluntary quality mark accredited by ENAC, according to UNE-EN ISO/IEC 17065, which complies with the requirements contained in the current Instruction for the reception of cements. This statistical assessment shows the outcomes within the evaluated period as summarized below:				

CHARACTERISTICS OF CEMENT

PROCESS CONTRIBUTION TO SUSTAINABILITY INDEX (ICPS)							98
RECYCLING INDEX (IR) (%)							9,96
Pre-consumer recycled content (%)							8,66
Post-consumer recycling content (%)							1,3
Nominal composition (declared by the producer) (%):							
Clinker	Pozzolana	Fly ash	Blast furnace slag	Limestone	Burnt shale	Silica fume	Other constituents
98							2

INSPECTION BY VARIABLES

Autocontrol samples

Number of samples 85

	Strength (MPa)		Setting time (min.)		
	a 2 días	a 28 días	Initial	Final	
Specification	≥ 30	≥ 52,5	≥ 45	≤ 720	Specification
Number of tests	85	77	85	85	Number of tests
Average value	43,8	70	217	285	Average value
Standard deviation	2,23	2,68	30	35	Standard deviation
Lower characteristic value	39,4	64,7	170	230	Lower absolute value
Upper characteristic value	47,3	74,2	264	340	Upper absolute value

Consumer´s risk < 3,25 %

Audit samples

Number of samples 10

	Strength (MPa)		Setting time (min.)		
	a 2 días	a 28 días	Initial	Final	
Specification	≥ 30	≥ 52,5	≥ 45	≤ 720	Specification
Number of tests	10	10	10	10	Number of tests
Average value	42,5	67,8	232	321	Average value
Standard deviation	1,67	3,29	37	39	Standard deviation
Lower characteristic value	39,77	63,05	170	255	Lower absolute value
Upper characteristic value	45,7	72,08	280	385	Upper absolute value

INSPECTION BY ATTRIBUTES (Physical and chemical characteristics):

Autocontrol samples

Number of samples 85

	Loss on Ignition (%)	Insoluble residue (%)	Chloride (%)	SO3 (%)	Soundness (mm)	
Specification	≤ 5	≤ 5	≤ 0,1	≤ 4	≤ 10	Specification
Number of tests	85	20	20	85	43	Number of tests
Average value	2,9	1,3	0,05	3,12	0,2	Average value
Nº of defaults	0	0	0	0	0	Nº of defaults
Nº of defaults admitted	4	0	0	4	1	Nº of defaults admitted

Audit samples

Number of samples 10

	Loss on Ignition (%)	Insoluble residue (%)	Chloride (%)	SO3 (%)	Soundness (mm)	
Specification	≤ 5	≤ 5	≤ 0,1	≤ 4	≤ 10	Specification
Number of tests	10	10	10	10	10	Number of tests
Average value	2,62	0,73	0,02	3,15	0,5	Average value
Nº of defaults	0	0	0	0	0	Nº of defaults
Nº of defaults admitted	0	0	0	0	0	Nº of defaults admitted

Complementary characteristic of water-soluble Cr(VI) is certified according to UNE EN 196-10 in accordance with the provisions of Regulation (EC) No. 1907/2006, entry 47. The water-soluble Cr(VI) content complies the limit of 0,0002%. Whether Cr(VI) reducing agent is being used, the compliance of this requirement is assessed at the end of its own shelf life period for such agent as declared by the manufacturer.

